

Pro Platinum

Property	Test Method	English	Metric
Color	Observed	Black	Black
Line Spacing	Observed	12 in	12 in
Polymer	Observed	Polypropylene	Polypropylene
Construction	Observed	Woven and Needle-punched	Woven and Needle-punched
Typical Weight	ASTM D-3776	4.1 oz/sy	140 GSM
Grab Tensile (MD)	ASTM D-4632	90 lbs	41 KG
Grab Tensile (CD)	ASTM D-4632	53 lbs	24 KG
Trapezoid Tear	ASTM D-4533	47 x 26 lbs	21 x 12 KG
Puncture	ASTM D-4833	61 lbs	28 KG
Water Permeability	ASTM D-4491	12 gpm/sf	480 LPM/M ²
Ultraviolet Exposure (% Strength Retained)	ASTM D-4355	>80% %	>80% %

DISCLAIMER: Descriptions regarding the products described herein are based solely upon information provided by the manufacturer and are provided for informational purposes only. **NOTHING CONTAINED HEREIN SHOULD BE CONSTRUED AS CREATING AN EXPRESSED OR IMPLIED WARRANTY, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS, EACH OF WHICH IS HEREBY DISCLAIMED. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF.** The final determination as to the suitability of any product of Hanes Geo Components in any particular application rests solely with the user. Hanes Geo Components reserves the right to alter or modify its products and descriptions at any time without notice.