



THE GROUND CONTROL LEADERS

PRODUCT DATA SHEET

MIRAFI 1160N

Mirafi® 1160N is a nonwoven geotextile composed of polypropylene fibers, which are formed into a stable network such that the fibers retain their relative position. 1160N is inert to biological degradation and resists naturally encountered chemicals, alkalis, and acids.

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value	
			MD	CD
Grab Tensile Strength	ASTM D 4632	kN (lbs)	1.69 (380)	1.69 (380)
Grab Tensile Elongation	ASTM D 4632	%	50	50
Trapezoid Tear Strength	ASTM D 4533	kN (lbs)	0.62 (140)	0.62 (140)
Mullen Burst Strength	ASTM D 3786	kPa (psi)	5098 (740)	
Puncture Strength	ASTM D 4833	kN (lbs)	1.05 (235)	
Apparent Opening Size (AOS)	ASTM D 4751	mm (U.S. Sieve)	0.150 (100)	
Permittivity	ASTM D 4491	sec ⁻¹	0.7	
Permeability	ASTM D 4491	cm/sec	0.20	
Flow Rate	ASTM D 4491	l/min/m ² (gal/min/ft ²)	2037 (50)	
UV Resistance (at 500 hours)	ASTM D 4355	% strength retained	70	

Physical Properties	Test Method	Unit	Typical Value
Weight	ASTM D 5261	g/m ² (oz/yd ²)	492 (14.5)
Thickness	ASTM D 5199	mm (mils)	3.8 (150)
Roll Dimensions (width x length)	--	m (ft)	4.5 x 45 (15 x 150)
Roll Area	--	m ² (yd ²)	209 (250)
Estimated Roll Weight	--	kg (lb)	114 (251)