



**THE GROUND CONTROL LEADERS**

# PRODUCT DATA SHEET

## MIRAFI 170N

Mirafi® 170N is a nonwoven geotextile composed of polypropylene fibers, which are formed into a stable network such that the fibers retain their relative position. Mirafi® 170N is inert to biological degradation and resists naturally encountered chemicals, alkalis, and acids.

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value	
			MD	CD
Grab Tensile Strength	ASTM D 4632	N (lbs)	801 (180)	801 (180)
Grab Tensile Elongation	ASTM D 4632	%	50	50
Trapezoid Tear Strength	ASTM D 4533	N (lbs)	334 (75)	334 (75)
CBR Puncture Strength	ASTM D 6241	N (lbs)	2003 (450)	
Apparent Opening Size (AOS) <sup>1</sup>	ASTM D 4751	mm (U.S. Sieve)	0.15 (100)	
Permittivity	ASTM D 4491	sec <sup>-1</sup>	1.2	
Flow Rate	ASTM D 4491	l/min/m <sup>2</sup> (gal/min/ft <sup>2</sup> )	4278 (105)	
UV Resistance (at 500 hours)	ASTM D 4355	% strength retained	70	

<sup>1</sup> ASTM D 4751: AOS is a Maximum Opening Diameter Value

Physical Properties	Test Method	Unit	Typical Value
Weight	ASTM D 5261	g/m <sup>2</sup> (oz/yd <sup>2</sup> )	251 (7.4)
Thickness	ASTM D 5199	mm (mils)	1.7 (67)
Roll Dimensions (width x length)	--	m (ft)	4.5 x 91 (15 x 300)
Roll Area	--	m <sup>2</sup> (yd <sup>2</sup> )	418 (500)
Estimated Roll Weight	--	kg (lb)	111 (245)